

# TEST REPORT

**Report No.:** BCTC2104762338-2R

Applicant: JW Mobile LLC

Product Name: broadcast light tripod with phone mount

Product Type: SKU 89149

**Tested Date:** 2021-04-26 to 2021-04-29

**Issued Date:** 2021-05-06

Shenzhen Bo



Co., Ltd.



No.: BCTC/RF-CH-00!

Page 1 of 7

Edition: A.1



Product Name	broadcast light tripod with phone mount
Testing type /model	SKU 89149
Additional type /model	SKU 89160, Model# 6965
Applicant	JW Mobile LLC
Address	140 58th Street, Brooklyn New York 11220 USA
Manufacturer	Telephone Est(HK) Co., Ltd
Address	Room706, 7F, Fuli Tianhe Commercial Building, Linhe East and Tianhe District,
	Guangzhou, China
Trademark	Primo
Sample Received Date	2021-04-26
Test Type	Entrustment Test
	California Proposition 65 Settlements:
Test Standard and	- Total Lead content
Requirements	- Phthalates content
751	- Total Cadmium content
	12,12,
Test Result	The samples were tested according to the entrusted requirements and test standard,
	and the test items of the test samples were qualified.

Tested by:

Chen

Approved by:

Saher Chen



## **Tested Sample/Part Description:**

- 1 White plastic
- 2 Black plastic
- 3 Black plastic
- 4 Black metal

## Test Result(s):

## ◆ Total Lead content

With reference to California proposition 65 settlements, methods CPSC-CH-E1001-08.3/ CPSC-CH-E1002-08.3 were used and total Lead content was determined by ICP-OES.

Tested Item	Result(s) Unit (mg/kg)				MDL	Limit
	1	2	3	4	Unit (mg/kg)	Unit (mg/kg)
Total Lead (Pb)	N.D.	N.D.	N.D.	N.D.	5	100

## Note:

-MDL = Method Detection Limit

-N.D. = Not Detected (<MDL)

-mg/kg = ppm = parts per million



#### **♦** Phthalates content

With reference to California Proposition 65 settlements, method CPSC-CH-C1001-09.4 was used and phthalates were determined by gas chromatograph with mass spectrometer (GC-MS).

Tested Item(s)		Result(s) %	3	MDL %	Limit %
Phthalates					1
Bis(2-ethylhexyl) Phthalate (DEHP)	N.D.	N.D.	N.D.	0.005	0.1
Dibutyl Phthalate (DBP)	N.D.	N.D.	N.D.	0.005	0.1
Butyl benzyl Phthalate (BBP)	N.D.	N.D.	N.D.	0.005	0.1
Diisononyl Phthalate (DINP)	N.D.	N.D.	N.D.	0.005	0.1
Diisodecyl Phthalate (DIDP)	N.D.	N.D.	N.D.	0.005	0.1
Di-n-hexyl Phthalate (DnHP)	N.D.	N.D.	N.D.	0.005	0.1
Di-n-octyl Phthalate (DNOP)	N.D.	N.D.	N.D.	0.005	0.1

## Note:

-MDL = Method Detection Limit

-N.D. = Not Detected (<MDL)

-%= Percentage by weight

#### **♦** Total Cadmium content

With reference to California proposition 65 settlements, methods CPSC-CH-E1001-08.3/ CPSC-CH-E1002-08.3 were used and total Cadmium(Cd) content was determined by ICP-OES.

Tested Item	Result(s) Unit (mg/kg)				MDL	Limit Unit (mg/kg)
	1	2	3	4	Unit (mg/kg)	Offit (Ing/kg)
Total Cadmium(Cd)	N.D.	N.D.	N.D.	N.D.	2	300

#### Note:

-MDL = Method Detection Limit

-N.D. = Not Detected (<MDL)

-mg/kg = ppm = parts per million



# Photograph of Sample



Fig.1




Fig.2

. : BCTC/RF-CH-005

Page 5 of 7

Edition: A.1





# **STATEMENT**

- 1. The equipment lists are traceable to the national reference standards.
- 2. The test report can not be partially copied unless prior written approval is issued from our lab.
- 3. The test report is invalid without stamp of laboratory.
- 4. The test report is invalid without signature of person(s) testing and authorizing.
- 5. The test process and test result is only related to the Unit Under Test.
- 6. The quality system of our laboratory is in accordance with ISO/IEC17025.
- 7. If there is any objection to report, the client should inform issuing laboratory within 15 days from the date of receiving test report.

#### Address:

1-2/F., Building B, Pengzhou Industrial Park, No.158, Fuyuan 1st Road, Tangwei, Fuhai Subdistrict, Bao'an District, Shenzhen, Guangdong, China

TEL: 400-788-9558

P. C.: 518103

FAX: 0755-33229357

Website: http://www.bctc-lab.com

E-Mail: bctc@bctc-lab.com.cn

\*\*\*\* END \*\*\*\*

: BCTC/RF-CH-005

Page / of /

Edition: A.1